

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 April 2005 (21.04.2005)

PCT

(10) International Publication Number
WO 2005/035628 A1

(51) International Patent Classification⁷: **C08G 77/00**

(21) International Application Number:
PCT/IB2004/003220

(22) International Filing Date: 4 October 2004 (04.10.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03022449.7 7 October 2003 (07.10.2003) EP

(71) Applicant (for all designated States except US): **CLARI-
ANT INTERNATIONAL LTD** [CH/CH]; Rothausstrasse
61, CH-4132 MuttENZ 1 (CH).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **DANNER, Bernard**
[FR/FR]; 8B, rue du Beau Site, F-68400 Riedisheim (FR).

(74) Agent: **DÜNNWALD, Dieter**; Clariant International Ltd,
Rothausstrasse 61, CH-4132 MuttENZ 1 (CH).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: **MULTIPLE QUATERNARY POLYSILOXANES**

(57) Abstract: The present invention concerns polysiloxanes having plural quaternary ammonium groups, their preparation and their use as softeners in the textile industry. Materials treated therewith exhibit a surprisingly high shear stability, an excellent, pleasant softness and improved sewability.

WO 2005/035628 A1

MULTIPLE QUATERNARY POLYSILOXANES

The present invention concerns polysiloxanes having plural quaternary ammonium
 5 groups, their preparation and their use as softeners in the textile industry.


There is extensive literature about silicone compounds having quaternary ammonium
 groups. These compounds are used for example as softeners in the textile industry, as
 surface-treating agents, as thickeners or in the cosmetic industry. WO 03/035721 A1
 10 for example discloses silicone compounds which contain quaternary ammonium groups
 and methods for their preparation.

There nevertheless continues to be a demand in the textile industry for softening
 substances possessing better shear stability and better hand than prior art compounds.

15

It has now been found that certain polysiloxanes having plural quaternary ammonium
 groups have surprisingly good properties when used as softeners in the textile industry
 and lead to products having high shearing stability and good hand.

20 The invention accordingly provides multiply quaternized polysiloxanes of the formula
 (S1)




S1

where

the sum total of (q + w) has a range of 10-1500, preferably of 15-600, and the q/w ratio has a range of 5-600, preferably of 10-400,

- 5 R is C₁-C₄-alkyl, linear or branched,
 R₁ is hydrogen, C₁-C₃-alkyl or C₁-C₃-alkoxy,
 R₂ is C₁-C₇-alkyl or benzyl,
 X is a direct bond


10 or



where

- 15 r is 1-4 and
 R₃ is C₁-C₇-alkyl or -NH-C₁-C₇-alkyl,

or




20

where


R₂ and r are each as defined above,
 R₄ is C₁-C₃-alkyl,

25


or



Y is



5 or



where


10 x is 1-4,

Z is C₂-C₄-alkylene, linear or branched and

A⁻ is CH₃OSO₃⁻, chloride, bromide, iodide or tosylsulfate⁻,

or of the formula (S2)

15



where

R, R₂ and A⁻ have the same meaning as in formula (S1),

20 m is 1 - 4,

p is 1 - 4, and



s is 5 - 1500, preferably 10-600.

Preference is given to compounds wherein


25

the sum total of (q + w) has a range of 15-600 and the q/w ratio has a range of 10-400,



- R is methyl, ethyl or propyl,
 R₁ is H, methyl, -OCH₃ or -OC₂H₅,
 R₂ is methyl or benzyl,
 5 R₃ is methyl or -NH-C₄H₉,
 R₄ is methyl,
 A⁻ is CH₃OSO₃⁻ or chloride,
 Z is C₃-alkylene, linear or branched,
 m is 3,
 10 p is 3,
 s is 10 - 600,
 r is 2, and
 x is 3.
- 15 Very particularly suitable polysiloxanes have the following structural units:



5





E2





E3

5




E4

6




5 The invention further provides for the preparation of the aforementioned polysiloxanes.

The formula (S1) compounds in which Y is



10

and X is




15 can be prepared by reaction of 3-(2-aminoalkylamino)alkyldialkoxymethylsilane with glycidylalkylamine (preparable by reaction of dialkylamine with epichlorohydrin) to form the corresponding silane and subsequent reaction of the resultant silanes with a)

polydimethylsiloxanediol or with octamethylcyclotetrasiloxane, and with b) tetraalkyl- or arylalkyl-ammonium hydroxide (for example benzyltrimethyl-, tetramethyl- or tetrabutyl-ammonium hydroxide) to form polysiloxanes with subsequent quaternization to the multiply quaternized siloxanes. Preferred starting substances are 3-(2-aminoethyl-amino)propyldimethoxymethylsilane, 3-(2-aminoethylamino)propyl-diethoxymethylsilane and glycidyldimethylamine, glycidyldiethylamine and glycidyldipropylamine. Examples thereof are the end products E1a and E3.

Quaternization can be effected using conventional quaternizing agents of the kind known per se for quaternizing tertiary amino groups, examples being alkyl halides or dialkyl sulphates, for example dimethyl sulphate, diethyl sulphate, or methyl chloride, ethyl chloride, methyl bromide, ethyl bromide or benzyl chloride. It is advantageous to use benzyl chloride or preferably a dialkyl sulphate for this purpose. To each particular quaternary ammonium ion formed the corresponding counterion (particularly chloride or alkylsulphate ion) is formed. Dimethyl sulfate is particularly preferred.

The formula (S1) polysiloxanes in which Y is




20

and X is a direct bond can be prepared by the reaction of 3-aminoalkyldialkoxymethylsilane with glycidyldialkylamine (preparable by reaction of dialkylamine with epichlorohydrin) to form the corresponding silane, and subsequent reaction of the resultant silanes with a) polydimethylsiloxanediol or with octamethylcyclotetrasiloxane, and with b) tetraalkyl- or arylalkyl-ammonium hydroxide (for example benzyltrimethyl-, tetramethyl- or tetrabutyl-ammonium hydroxide) to form polysiloxanes with subsequent quaternization to the multiply quaternized siloxanes.

Preferred starting substances are 3-aminopropyldiethoxymethylsilane, 3-aminopropyldimethoxymethylsilane and glycidyldimethylamine, glycidyldiethylamine and glycidyldipropylamine. Examples thereof are the end products E2 and E4.

The formula (S1) polysiloxanes in which Y is $\text{-(CH}_2\text{)}_x\text{-}$ and X is



can be prepared by reaction of N'-[3-(dialkylamino)alkyl]-N,N-dialkylalkane-1,3-diamine with dialkoxy(3-glycidyloxyalkyl)methylsilane and subsequent reaction with polydi-
 5 methylsiloxanediol or with octamethylcyclotetrasiloxane with subsequent quaterniza-
 tion.

Preferred starting substances are N'-[3-(dimethylamino)propyl]-N,N-dimethylpropane-
 1,3-diamine, diethoxy(3-glycidyloxypropyl)methylsilane and dimethoxy(3-glycidyloxy-
 10 propyl)methylsilane. As an example thereof there may be mentioned the end product
 E5.

The compounds of the formula (S2) can be prepared for example by reaction of
 octamethylcyclotetrasiloxane with 1,1,3,3-tetraalkyldisiloxane, preferably 1,1,3,3-
 15 tetramethyldisiloxane, reaction of the reaction product with an allyl glycidyl ether and a
 hydrosilylation catalyst, reaction of this reaction product with N,N,N',N'-tetraalkyl-
 dialkylene triamine, preferably N,N,N',N'-tetramethyldipropylenetriamine, to form the
 polysiloxane, and subsequent quaternization. As an example thereof there may be
 mentioned the end product E6.

20 Instead of octamethylcyclotetrasiloxane it is also possible to use penta- or hexamethyl-
 cyclotetrasiloxane or mixtures thereof.

The compounds according to the invention are very useful as softeners in the treatment
 25 of textiles, specifically for cotton and polyester. The materials treated therewith exhibit
 a surprisingly high shearing stability, an excellent, pleasant softness and improved
 sewability. The products can also be used in the form of microemulsions.

30 EXAMPLES


The examples which follow illustrate the invention. Parts are by weight.


A. SILICONE OILS**1. Preparation of silanes (I) and (II)****1.1 Preparation of glycidyldiethylamine**

298.00 parts of diethylamine are mixed with 12.25 parts of water. 377.60 parts of epichlorohydrin are then added dropwise at 20°C within 10 hours with stirring. This is followed by further stirring at 20°C for 10 hours before 506.7 parts of 30% by weight aqueous sodium hydroxide solution are added dropwise. The stirrer is switched off after 3 hours (15-20°C). An organic phase forms (501.5 parts) and is separated off. It consists of about 384.0 parts of glycidyldiethylamine, 60.0 parts of N,N,N',N'-tetraethyl-1,3-diamino-2-hydroxypropane, 25.0 parts of water, 24.5 parts of N,N-diethyl-2-hydroxy-3-chloropropaneamine, 1.0 part of sodium chloride and 7.0 parts of 3-dimethylamino-2-hydroxy-1-propanol.

1.2 Preparation of silane (I)

309.00 parts of 3-(2-aminoethylamino)propyldimethoxymethylsilane are mixed with 505.40 parts of the freshly prepared organic phase of 1.1 with stirring and heated to 60°C. A slightly exothermic reaction takes place. The exothermic reaction ceases after about 2 hours and the batch is left to react further at 60°C for 4 hours. It is then cooled down to room temperature. Glycidyl groups are no longer titratable. An alkylation of the primary amino group has taken place. 814.4 parts are obtained of a silane mixture (I) having the following main components:







Silane mixture (I)

5 1.3 Preparation of silane (II)

286.50 parts of 3-aminopropyldiethoxymethylsilane are mixed together with 505.40 parts of the freshly prepared organic phase at room temperature with stirring and heated to 60°C. An exothermic reaction takes place, the temperature being held at 60°C by cooling. As soon as the exothermic reaction is over, the batch is allowed to react further at 60°C for 4 hours and is then cooled down to room temperature. Glycidyl groups are no longer titratable. An alkylation of the primary amino groups of the silane has taken place. 791.9 parts are obtained of a silane mixture (II) having the following main components:





Silane mixture (II)

5 2. Preparation of silanes (III) and (IV)


2.1 Preparation of glycidyldipropylamine

404.0 parts of dipropylamine are mixed with 12.0 parts of water and cooled down to 20°C. 370.0 parts of epichlorohydrin are then added dropwise within 60 minutes while the temperature is held between 18 and 20°C. After a subsequent-stirring time of about 20 hours at 20°C 673.4 parts of sodium methoxide-methanol solution, 30%, are added dropwise in 60 minutes. Immediately a sodium chloride precipitate forms as a result of the formation of the glycidyl compound. After the sodium chloride has been removed by filtration first methanol and then the resultant glycidyldipropylamine are distilled off. 470 g of glycidyldipropylamine having an equivalent weight of 161.8 (97% pure) are obtained between 65 and 80°C at 8 to 14 mbar (yield: 72.5%).


2.2 Preparation of silane (III)

309.00 parts of 3-(2-aminoethylamino)propyldimethoxymethylsilane are reacted with 485.4 parts of glycidyldipropylamine, prepared as per 2.1, exactly as described under 1.2 to obtain 794,4 parts of silane (III) of the following structure:

12

**Silane (III)**5 2.3 Preparation of silane (IV)

286.50 parts of 3-aminopropyldiethoxymethylsilane are reacted with 485.4 parts of glycidydipropylamine, prepared as per 2.1, exactly as described under 1.2, to obtain 771.9 parts of silane (IV) of the following structure:




10

Silane (IV)3. Preparation of silane (V)

15 187.0 parts of N'-[3-(dimethylamino)propyl]-N,N-dimethylpropane-1,3-diamine are heated to 80°C. 248.0 parts of diethoxy(3-glycidyloxypropyl)methylsilane are then added dropwise while the temperature is held at 80°C. After the glycidyl has been added, the reaction is allowed to proceed at 130°C for a further 4 hours, to obtain 435.0 parts of silane (V) of the following structure:

20

**Silane (V)**

4. Preparation of polysiloxane (I)

691.0 parts of polydimethylsiloxanediol (viscosity 80 cp = 0.08 Pas)
(Polydimethylsiloxanediol L), 28.2 parts of silane (I) (reaction mixture I) and also
5 5.5 parts of a 40% solution of benzyltrimethylammonium hydroxide in methanol
are mixed together and heated to 80°C with stirring. After 3 hours at 80°C the
batch is evacuated down to about 200 mbar residual pressure and heated to
150°C at this pressure in the course of 60 minutes. This is followed by evacuation
to about 50 mbar residual pressure and, after 60 minutes under these conditions,
10 cooling to room temperature under constant residual pressure (50 mbar) to obtain
about 707.0 parts of polysiloxane (I) (viscosity 2660 cp = 2.66 Pas) and
15.0 parts of distillate.

5. Preparation of polysiloxane (II)

15 691.0 parts of polydimethylsiloxanediol (viscosity 80 cp = 0.08 Pas)
(Polydimethylsiloxanediol L), 38.73 parts of silane (II) (reaction mixture II) and
also 5.4 parts of a 40% solution of benzyltrimethylammonium hydroxide in
methanol are mixed together and heated to 80°C with stirring. After 3 hours at
80°C the batch is evacuated down to about 200 mbar residual pressure and
20 heated to 150°C at this pressure in the course of 60 minutes. This is followed by
evacuation to 50 mbar residual pressure and distillation for 60 minutes at this
pressure and at 150°C, to obtain about 15.8 parts of distillate. After cooling to
room temperature under vacuum about 715.4 parts of polysiloxane (II (viscosity
900 cp = 0.9 Pas) are obtained.

25

6. Preparation of polysiloxane (III)

691.0 parts of polydimethylsiloxanediol, 55.1 parts of silane (III) and 3.2 parts of a
40% solution of benzyltrimethylammonium hydroxide in methanol are heated to
80°C in a closed vessel. After 4 hours at 80°C the pressure reactor is equipped
30 with a distillation bridge and evacuated to 200 mbar residual pressure. As soon
as this pressure is obtained, the reactor is heated to 150°C in the course of 60
minutes. The residual pressure is then lowered to 50 mbar with continued stirring
at 150°C for 1 hours. This is followed by cooling to room temperature at 50 mbar
residual pressure to obtain about 728.0 parts of polysiloxane (III) having a
35 viscosity of 2150 cp = 2.15 Pas.

7. Preparation of polysiloxane (IV)

691.0 parts of Polydimethylsiloxanediol L, 38.0 parts of silane (IV) and 0.7 part of a 40% solution of benzyltrimethylammonium hydroxide in methanol are heated to 80°C and left to react at this temperature for 3 hours. This is followed by
5 evacuation to 900 mbar residual pressure and heating to 150°C at this pressure in the course of 60 minutes. This is followed by full evacuation (50 mbar residual pressure) before the temperature is held at 150°C for 30 minutes. The reactor is then cooled down to room temperature, depressurized to atmospheric with nitrogen and emptied to obtain 694.1 parts of polysiloxane (IV) having a viscosity
10 of 1760 cp = 1.76 Pas.


8. Preparation of polysiloxane (V)

The procedure for polysiloxane (IV) is repeated except that 32.1 parts of silane (V) are used instead of 38.0 parts of silane (IV). 696.2 parts of polysiloxane (V)
15 having a viscosity of 1200 cp = 1.2 Pas are obtained.

9. Preparation of polysiloxane (VI)

419.3 parts of octamethylcyclotetrasiloxane (D4) and 25.3 parts of 1,1,3,3-tetramethyldisiloxane are heated to 80°C together with 0.43 part of
20 trifluoromethanesulphonic acid. After 4 hours at 80°C the batch is admixed with 0.43 part of magnesium oxide, evacuated to 50 mbar residual pressure and heated to 150°C under these conditions. After 30 minutes at 150°C and 50 mbar the batch is cooled down to room temperature under vacuum and discharged through a paper filter to obtain 405.7 parts of an H-terminated
25 polydimethylsiloxane. This product is then heated back up to 80°C under nitrogen. As soon as 80°C is attained, 35 ml of a 3% (based on platinum) of a platinum-cyclovinyldimethylsiloxane complex (in cyclic methylvinylsiloxanes) (hydrosilylation catalyst) are added before 42.6 parts of allyl glycidyl ether are added dropwise in the course of about 60 minutes. As soon as the Si-H groups
30 have reacted (if not, some more catalyst is added), the batch is heated to 100°C, evacuated to 50 mbar residual pressure and, after 60 minutes at 100°C, cooled down to room temperature 50 mbar to obtain 443.0 parts of glycidyl-terminated polydimethylsiloxane having an equivalent weight of 1334 (equivalent weight for a glycidyl group). 62.1 parts of N,N,N',N'-tetramethyldipropylenetriamine are then
35 added and heated to 130°C. As soon as the glycidyl groups are no longer

titratable the batch is cooled down to room temperature to obtain 505.1 parts of polysiloxane (VI) having the following general formula:



5


Polysiloxane (VI)

B. END PRODUCTS

1. Based on polysiloxane (I)

200.0 parts of polysiloxane (I) are emulsified with 50.0 parts of tridecanol poly-6,5-ethylene glycol (emulsifier I) and 50.0 parts of water and heated to 40°C. As soon as this temperature is reached, 10.04 parts of dimethyl sulphate are added dropwise. After 6 hours at 40°C twice 200 parts of water are added followed by 40 parts of hexylene glycol. This is followed by the addition of a further 70 parts of emulsifier (I) and 180 parts of water to obtain 1000.0 parts of a 20% microemulsion of the fully quaternized polysiloxane (I) (end product E1).

15




20

End product E1

2. Based on polysiloxane (I)

The procedure for end product E₁ is repeated except that only 6.02 parts of dimethyl sulphate are added instead of 10.04 parts and prior to the heating to 40°C 52.0 parts of water are used instead of 50 parts after the addition of 50 parts of emulsifier (I) and in addition 2.0 parts of dimethyl dicarbonate are added. As soon as CO₂ evolution has taken place, the batch is heated to 40°C and further processed to obtain 1000.0 parts of a 20% microemulsion of a polysiloxane E1a having the following functional groups:




End product E1a

3. Based on polysiloxane (II)

200.0 parts of polysiloxane (II) are mixed with 40.0 parts of hexylene glycol and heated to 40°C. 8.86 parts of dimethyl sulphate are then added dropwise and reacted at 40°C for 6 hours. This is followed by the addition of 115.0 parts of emulsifier (I) and - as soon as a homogeneous mixture is present - of 390.0 parts of water at 60°C to form a microemulsion, which is cooled to room temperature by addition of 247.0 parts of water and by external cooling to obtain about 1000 parts of microemulsion (E2). The siloxane of E2 contains the following functional groups:

17

**End product E2**5 **4. Based on polysiloxane (III)**



The procedure for E2 is repeated with the following amounts and reactants:

	Polysiloxane (III)	200.0 parts
	Water (1)	52.0 parts
10	Emulsifier (I) (1)	50.0 parts
	Dimethyl dicarbonate	3.8 parts
	Dimethyl sulphate	10.8 parts
	Water (2)	400.0 parts
	Hexylene glycol	40 parts
15	Emulsifier (I) (2)	70 parts
	Water (3)	174 parts

About 1000.0 parts of emulsion E3 are obtained. The emulsified polysiloxane has the following functional groups:

20


18

**End product E3****5. Based on polysiloxane (IV)**

The procedure for E3 is repeated with the following amounts and reactants:

	Polysiloxane (IV)	200.0 parts
	Hexylene glycol	40.0 parts
10	Dimethyl sulphate	8.1 parts
	Emulsifier (I)	115.0 parts
	Water (1)	390.0 parts
	Water (2)	247.0 parts

15 About 1000.0 parts of emulsion E4 are obtained. The emulsified polysiloxane has the following functional groups:




20

End product E4

6. Based on polysiloxane (V)


The procedure for E4 is repeated using polysiloxane (V) in place of (IV). About 1000.0 g of end product E5 are obtained. The emulsified polysiloxane has the following functional groups:

5

**End product E5****7. Based on polysiloxane (VI)**

200.0 parts of polysiloxane (VI) are mixed with 100.0 parts of hexylene glycol and then reacted with 49.7 parts of dimethyl sulphate at 40°C for 4 hours. 751 parts of water are added to obtain 1000.0 parts of end product E6. The self-dispersed polysiloxane has the following structure:

15

**End product E6**

APPLICATION EXAMPLES

- 1) A textile substrate is padded at room temperature to a 100% dry weight increase with an aqueous liquor which contains a g/l of the products E₁ to E₆, b g/l of aqueous 50% dimethyldihydroxyethyleneurea solution and c g/l of magnesium chloride hexahydrate. The padded material is subsequently subjected to a thermal treatment.

<u>Appl. Ex.</u>	<u>Substrate</u>	<u>Product E</u>	<u>Composition of liquor</u>			<u>Thermal treatment</u>	
						<u>Temp.</u>	<u>Total duration</u>
			<u>a</u>	<u>b</u>	<u>c</u>		
1.1	T ₁	E1	20	0	0	140°C	80 sec.
1.2	T ₁	E1a	40	0	0	140°C	80 sec.
1.3	T ₂	E2	20	100	15	175°C	90 sec.
1.4	T ₂	E2	40	100	15	175°C	90 sec.
1.5	T ₃	E2	30	0	0	140°C	80 sec.
1.6	T ₄	E3	30	0	0	130°C	80 sec.
1.7	T ₅	E4	30	0	0	140°C	90 sec.
1.8	T ₆	E5	30	0	0	140°C	90 sec.
1.9	T ₂	E6	30	100	15	175°C	90 sec.

- T₁ cotton tricot, interlock, bleached, unbrightened
- T₂ cotton tricot, interlock, bleached
- T₃ polyester/cotton (50/50) intimate blend, tricot, dyed with reactive and disperse dyes
- T₄ polyester fabric, dyed with disperse dyes
- T₅ cotton gabardine, dyed with reactive dyes
- T₆ cotton gabardine, bleached, mercerized

2. 1 kg of the substrate to be finished (tubular textile material, cotton single jersey, blue) is treated with finishing agents (products E1 to E7) on a Mathis (Switzerland) laboratory jet at 40°C and a liquor ratio of 8:1. Liquor circulation rate is 60 l/min and treatment time is 20 minutes. The water has 10° of German hardness (according to German Industrial Specification DIN 53905) and a pH of 5


(set with sodium carbonate or acetic acid). After treatment, the substrate is whizzed and dried at 140°C for 90 seconds.

The textiles treated as per 1) and 2) exhibit excellent, pleasant softness. Sewability is
5 distinctly improved.

CLAIMS

1. Multiply quaternized polysiloxanes of the formula (S1)

5



S1

where

the sum total of (q + w) has a range of 10-1500 and the q/w ratio has a range of 5-600,


R is C₁-C₄-alkyl, linear or branched,

R₁ is hydrogen, C₁-C₃-alkyl or C₁-C₃-alkoxy,

R₂ is C₁-C₇-alkyl or benzyl,

X is a direct bond

or




where

r is 1-4 and

R₃ is C₁-C₇alkyl or -NH-C₁-C₇alkyl,

23

or




5

where


 R_2 and r are each as defined above, R_4 is C_1 - C_3 -alkyl,

10

or


 Y is

15



or

20




where

 x is 1-4, Z is C_2 - C_4 -alkylene, linear or branched and

25

 A^- is $\text{CH}_3\text{OSO}_3^-$, chloride, bromide, iodide or tosylsulfate⁻,

or of the formula (S2)



where

R , R_2 and A^- have the same meaning as in formula (S1),


- 5 m is 1 - 4,
 p is 1 - 4, and
 s is 5 - 1500

- 10 2. Multiply quaternized polysiloxanes according to Claim 1 wherein
 the sum total of $(q + w)$ has a range of 15-600 and the q/w ratio has a range of
 10-400,

- 15 R is methyl, ethyl or propyl,
 R_1 is H, methyl, $-OCH_3$ or $-OC_2H_5$,
 R_2 is methyl or benzyl,
 R_3 is methyl or $-NH-C_4H_9$,
 R_4 is methyl,
 Z is C_3 -alkylene, linear or branched,
 A^- is $CH_3OSO_3^-$ or chloride,
 m is 3,
 p is 3,
 s is 10 - 600,
 r is 2, and
 x is 3.
- 25


25

3. Multiply quaternized polysiloxanes according to Claim 1 or 2 having structural units of the formula E1



5


or having structural units of the formula E1a



10


4. Multiply quaternized polysiloxanes according to Claim 1 or 2 having structural units of the formula E2

26



E2.


5. Multiply quaternized polysiloxanes according to Claim 1 or 2 having structural units of the formula E3




E3.

- 10 6. Multiply quaternized polysiloxanes according to Claim 1 or 2 having structural units of the formula E4


27



7. Multiply quaternized polysiloxanes according to Claim 1 or 2 having structural units of the formula E5




8. Multiply quaternized polysiloxanes according to Claim 1 or 2 of the formula E6



9. Process for preparing multiply quaternized polysiloxanes of the formula (S1) according to any one of Claims 1 to 6, characterized in that the following reactions are carried out:

- 5 A) reaction of dialkylamine with epichlorohydrin to form a glycidyldialkylamine,
 B) reaction of the glycidyldialkylamine with 3-aminoalkyldialkoxymethylsilane or with 3-(2-aminoalkylamino)alkyldialkoxymethylsilane to form the corresponding silanes,
 10 C) reaction of the resultant silanes with polydimethylsiloxanediol or with octamethylcyclotetrasiloxane or with tetraalkyl- or aryltrialkyl-ammonium hydroxide to form polysiloxanes, with subsequent quaternization to form the multiply quaternized polysiloxanes.

- 15 10. Process for preparing multiply quaternized polysiloxanes of the formula (S1) where Y is $-(CH_2)_x-$ and X is



- 20 characterized in that the following reactions are carried out:

- A) reaction of N'-[3-(dialkylamino)alkyl]-N,N-dialkylalkane-1,3-diamine with dialkoxy(3-glycidyloxyalkyl)methylsilane,
 B) reaction of the reaction product from A) with polydimethylsiloxanediol or with octamethylcyclotetrasiloxane, with subsequent quaternization.

25

11. Process for preparing multiply quaternized polysiloxanes of the formula (S2) according to Claims 1 or 2, characterized in that the following reactions are carried out:

- 30 A) reaction of octaalkylcyclotetrasiloxane with 1,1,3,3-tetraalkyldisiloxane,
 B) reaction of the reaction product from A) with an allyl glycidyl ether and a hydrosilylation catalyst;
 C) reaction of the reaction product from B) with N,N,N',N'-tetraalkyldialkylenetriamine to form the polysiloxane and subsequent
 35 quaternization.

12. Use of multiply quaternized polysiloxanes according to Claims 1 to 8 as a softener in the textile industry.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB2004/003220

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08G77/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 100 04 321 A (WACKER CHEMIE GMBH) 9 August 2001 (2001-08-09) page 2, line 64 - page 4, line 4 abstract; claims 1-6; examples 1-6	1-12
X	WO 03/080007 A (CIBA SC HOLDING AG ; CHROBACZEK HARALD (DE); ELDER STEWART TODD (US);) 2 October 2003 (2003-10-02) page 1, line 20 - page 4, line 2 abstract; claims 1-20; examples 1-4	1-12
X	WO 03/029351 A (CHROBACZEK HARALD ; LINDMAIR GABRIELE (DE); CIBA SPEZIALITAETENCHEMIE) 10 April 2003 (2003-04-10) page 2, line 12 - page 3, line 15 abstract; claims 1-10; examples 1-4	1-12
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

17 November 2004

Date of mailing of the international search report

23/11/2004

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Glomm, B

INTERNATIONAL SEARCH REPORT

International Application No

.../IB2004/003220

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 618 525 A (BUENNING EINHARD) 8 April 1997 (1997-04-08) the whole document	1-12
P, X	DE 102 14 290 A (GE BAYER SILICONES GMBH & CO) 9 October 2003 (2003-10-09) paragraph '0013! - paragraph '0032! abstract; claims 1-26; examples A-E	1-12
Y	US 5 725 736 A (SCHROEDER WEN ZYO ET AL) 10 March 1998 (1998-03-10) column 1, line 19 - column 2, line 26 abstract; claims 1-14; examples 1,2	1-12
Y	WO 02/10259 A (SOCKEL KARL HEINZ ; LANGE HORST (DE); WAGNER ROLAND (DE); FIRSTENBERG) 7 February 2002 (2002-02-07) page 3, line 24 - page 6, line 6 abstract; claims 1-22; examples 1-3	1-12
A	US 6 482 969 B1 (HELMRICK LIZA RUTH ET AL) 19 November 2002 (2002-11-19) cited in the application column 2, line 19 - column 3, line 24 abstract; claims 1-22; examples 1-8	1-12

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

.../IB2004/003220

Patent document cited in search report			Publication date	Patent family member(s)		Publication date
DE 10004321	A	09-08-2001	DE	10004321 A1		09-08-2001
WO 03080007	A	02-10-2003	WO	03080007 A1		02-10-2003
WO 03029351	A	10-04-2003	WO EP	03029351 A1 1432765 A1		10-04-2003 30-06-2004
US 5618525	A	08-04-1997	DE AT EP JP US	4426794 C1 143797 T 0697208 A1 8040839 A 5690129 A		06-07-1995 15-10-1996 21-02-1996 13-02-1996 25-11-1997
DE 10214290	A	09-10-2003	DE	10214290 A1		09-10-2003
US 5725736	A	10-03-1998	AU AU CA EP WO ZA	714099 B2 4893197 A 2267176 A1 0934445 A1 9819012 A1 9708500 A		16-12-1999 22-05-1998 07-05-1998 11-08-1999 07-05-1998 26-03-1998
WO 0210259	A	07-02-2002	AU CA WO EP JP US	8396301 A 2422903 A1 0210259 A1 1311590 A1 2004519528 T 2004138400 A1		13-02-2002 19-03-2003 07-02-2002 21-05-2003 02-07-2004 15-07-2004
US 6482969	B1	19-11-2002	BR EP WO	0213623 A 1440113 A1 03035721 A1		14-09-2004 28-07-2004 01-05-2003